


# Bambu TREATMENT



For durability, bamboo needs to be treated against insects (borers and termites) and fungal attacks.



Culms should be treated with boron solution for at least two weeks. It's used against borers and moulds.

**2** mixing 2,5 grams of Borax and 2,5 grams of Boric Acid into 100cc of water



**1**

Steeping method of preservation by using a mix of chemicals right after cutting the poles.



bamboo infected by borers



It is necessary to dry the treated bamboo for (ideally) two weeks under a shelter or with low humidity to prevent fungal attack.

Bamboo is skinned to retain a uniform color. Strips are produced to function as reinforcement in cement applications.



Buho is treated before becoming roofing material. Buho can be crafted to ensure waterproof roof corners.

